



Wall Products International, INC.

201 NE 21st St, Fort Worth, Tx 76164

phone: 800.446.7124 or 817.626.1987

fax: 817.626.0821

www.murcowall.com email: murco@murcowall.com

SPECIFICATION AND DATA SHEET

PRODUCT NAME:

Murco M 101 Aggregated Texture

MANUFACTURER:

Murphy Wall Products International, Inc.
201 NE 21st St, Fort Worth, Tx, 76164
800.446.7124

ADVANTAGES:

- Covers Cracks and Blemishes
- Choice of Finishes
- Superior Aggregate
- Easy to Apply
- Reduces Overall Cost

PRODUCT DESCRIPTION:

A powder product with a perlite aggregate which produces a sand like texture. Designed for use on interior walls and ceilings. Can be used on gypsum panels, wood, concrete and plaster. This product is designed to be painted.

SURFACES PREPARATION:

Surface must be clean, dry and free of grease. Stained or smoked wallboard should be primed with stain killing primer. Prime metal, tie wires etc. with rust inhibitive primer. Glossy surfaces should be sanded, dulled, or primed. New concrete patching compound should also age 60 days before being covered (some concrete patching compound should also age 60 days.) Conceal drywall joints using Murco Light, Medium, or Heavy Weight joint compound and re-inforcing tape. Fill all fastener depressions, scuffs, and scratches with joint compound. After all surfaces are completely dry, apply a prime coat of high solid latex flat wall paint. This will not prevent migrating stains (rust, water, stains, etc.) from leaching to the surface.

MIXING:

Pour 2/3 of recommended amount of tap water into a clean vessel. Mix in texture using a variable speed power mixer. Allow to soak for 15 minutes. Then remix adding small amounts of water or texture until desired spray consistency is achieved. Do not over thin, overthinning causes aggregate separation, poor hide, lack of adhesion, texture variation and texture fallout during application. Joint compounds such as M300, M1200, M500, and M700 can be added to increase surface hardness and spraying properties, but the final texture will be less aggregated. Latex paint can also be added. They can be used to change the color, to increase the surface hardness and give better wet and dry hide.

APPLICATION:

Use acoustical spray equipment with either pole guns or binks 7E 2 guns. This equipment is manufactured by companies such as Murco Wall Products, Spray Force, Spray King, etc. Hopper type applicator may also be used. Use 3/4" to 1" material hose, and 3/8" atomizing hose. Keep pressure as low as needed. High pressure will cause excessive fallout during application. Do not exceed recommended coverage (300-400 per bag) as this will lead to poor hide, color differences, and variations in base suction. Two coats may be required on extremely porous surfaces. Let first



coat dry thoroughly before applying second. Maintain 55°F minimum air and surfaces temperature during application and until surface is dry.

PRODUCT DATA:

Color Bright White

Drying Time Dries to touch in 30 to 60 minutes (depending on air temperature and humidity)

Storage Store in a cool, dry place and seal open bags.

Packaging 25 lb. and 45lb. bag

Coverage M 101 covers 350 - 450 sq ft per 45 lb bag depending on desired finish.

PRECAUTIONS:

DO NOT ingest. A NIOSH approved nuisance dust respirator should be used if the air is dusty.

CAUTION: KEEP OUT OF REACH OF CHILDREN

DO NOT TAKE INTERNALLY

DO NOT FREEZE

MADE IN THE U.S.A